

Stainless Steel Balls



Numero di prodotto	Diametro della palla	Materiale	Tolleranza del diametro	Durezza	Temperatura massima	Grado	MOQ	Pacchetto	Certificato	Colore
AISI 440C Stainless Steel Balls 24 mm	24 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 18 mm	18 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 16 mm	16 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 15 mm	15 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 14 mm	14 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 13 mm	13 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 12 mm	12 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery

Stainless Steel Balls

AISI 316L Stainless Steel Balls 12 mm	12 mm	316L Stainless Steel	-0.013mm to 0.013mm	Rockwell B90	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 304 Stainless Steel Balls 12 mm	12 mm	304 Stainless Steel	-0.0127mm to 0.0127mm	Rockwell C25 (Hard)	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 10 mm	10 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 316L Stainless Steel Balls 10 mm	10 mm	316L Stainless Steel	-0.013mm to 0.013mm	Rockwell B90	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 304 Stainless Steel Balls 10 mm	10 mm	304 Stainless Steel	-0.0127mm to 0.0127mm	Rockwell C25 (Hard)	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 9 mm	9 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 8 mm	8 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 316L Stainless Steel Balls 8 mm	8 mm	316L Stainless Steel	-0.013mm to 0.013mm	Rockwell B90	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 304 Stainless Steel Balls 8 mm	8 mm	304 Stainless Steel	-0.0127mm to 0.0127mm	Rockwell C25 (Hard)	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 7 mm	7 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 316L Stainless Steel Balls 7 mm	7 mm	316L Stainless Steel	-0.013mm to 0.013mm	Rockwell B90	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery

Stainless Steel Balls

AISI 304 Stainless Steel Balls 7 mm	7 mm	304 Stainless Steel	-0.0127mm to 0.0127mm	Rockwell C25 (Hard)	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 6 mm	6 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 316L Stainless Steel Balls 6 mm	6 mm	316L Stainless Steel	-0.013mm to 0.013mm	Rockwell B90	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 304 Stainless Steel Balls 6 mm	6 mm	304 Stainless Steel	-0.0127mm to 0.0127mm	Rockwell C25 (Hard)	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 5 mm	5 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 316L Stainless Steel Balls 5 mm	5 mm	316L Stainless Steel	-0.013mm to 0.013mm	Rockwell B90	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 304 Stainless Steel Balls 5 mm	5 mm	304 Stainless Steel	-0.0127mm to 0.0127mm	Rockwell C25 (Hard)	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 4 mm	4 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 316L Stainless Steel Balls 4 mm	4 mm	316L Stainless Steel	-0.013mm to 0.013mm	Rockwell B90	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 304 Stainless Steel Balls 4 mm	4 mm	304 Stainless Steel	-0.0127mm to 0.0127mm	Rockwell C25 (Hard)	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
AISI 440C Stainless Steel Balls 3.5 mm	3.5 mm	440C Stainless Steel	-0.0025mm to 0.0025mm	HRC60-65	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery

Stainless Steel Balls

AISI 316L Stainless Steel Balls 3.5 mm	3.5 mm	316L Stainless Steel	-0.013mm to 0.013mm	Rockwell B90	800° F 427°C	G10	1PCS	Stadard	Rohs	silvery
---	--------	----------------------------	---------------------------	-----------------	-------------------	-----	------	---------	------	---------